



Plasto Ferrite Flessibile

Spessore/Thickness	0,5 mm	
Grade	surface gauss	holding force(g/cm ²)
GLF 04	240	≥ 24
GLF 11	330	≥ 43

Spessore/Thickness	1.0mm	
Grade	surface gauss	holding force(g/cm ²)
GLF 04	360	44
GLF 11	490	80

Spessore/Thickness	1.5 mm	
Grade	surface gauss	holding force(g/cm ²)
GLF 04	475	59
GLF 11	550	102

Spessore/Thickness	2,00 mm	
Grade	surface gauss	holding force(g/cm ²)
GLF 04	500	67
GLF 11	590	113

Spessore/Thickness	3,00 mm	
Grade	surface gauss	holding force(g/cm ²)
GLF 04	620	73
GLF 11	700	115

