



TABELLA GRADI PLASTO FERRITE FLESSIBILE

Material Type	Magnetic Properties				Physical Properties					
Grade	Br (Gs)	Hcb (Oe)	Hcj (Oe)	BH max (MGOe)	TS (Mpa)	Eb (%)	XHS-D	Density (g/m ³)	Weight reduction by heat (%)	Temp. Range (°C)
GLF 04	1550-1800	1100-1500	1800-2500	0,50-0,65	>3,5	>30	30-50	3,65-3,80	<2,0	-40/85
GLF 11	2300-2500	2050-2350	>2500	1,30-1,50	>3,5	>30	30-50	3,65-3,80	<2,0	-40/85
GLF 10N	2100-2300	1900-2200	>2500	1,15-1,35	>2,5	>20	30-45	3,60-3,75	<2,0	-40/100
GLF 11N	2300-2500	2050-2350	>2500	1,30-1,50	>2,5	>20	30-45	3,60-3,75	<2,0	-40/100
GLF 12	2400-2600	2000-2350	>2200	1,45-1,65	>3,5	>30	30-50	3,65-3,80	<2,0	-40/85
GLF 12N	2300-2500	2150-2400	>3200	1,35-1,55	>2,5	>20	30-45	3,60-3,75	<2,0	-40/100
GLF 13	2400-2600	2450-2450	2800-3500	1,45-1,65	>3,5	>30	30-50	3,65-3,80	<2,0	-40/85
GLF 13B	2500-2700	2100-2400	2600-3000	1,50-1,70	>3,5	>30	30-50	3,65-3,80	<2,0	-40/85
GLF 13BN	2400-2600	2100-2400	2600-3000	1,45-1,65	>2,5	>20	30-45	3,60-3,75	<2,0	-40/100
GLF 13N	2400-2600	2150-2450	2800-3500	1,45-1,65	>2,5	>20	30-45	3,60-3,75	<2,0	-40/100
GLF 13H	2400-2600	2150-2450	3500-4200	1,45-1,65	>2,5	>20	30-45	3,60-3,75	<2,0	-40/85
GLF 13HN	2400-2600	2150-2450	2500-4200	1,45-1,65	>2,5	>20	25-45	3,60-3,75	<2,0	-40/100
GLF 14	2550-2750	2100-2300	>2300	1,55-1,75	>3,5	>30	30-50	3,65-3,80	<2,0	-40/85

